

LEIGHTON BUZZARD DA 30

GRADATION ANALYSIS TEST REPORT

Source: LEIGHTON BUZZARD

Geology: Lower Greensand

Test Method: Wash grading to BS 812 : Section 103.1: 1985

SAMPLE ANALYSIS

Sieve Size Microns	Percent Passing
1000	99.7
600	86.2
500	61.4
355	20.2
300	6.2
250	1.2
180	0.2
150	0.1

Chemical Analysis

	Typical %
SiO ₂	92.03
FeO ₂ O ₃	5.36
Al ₂ O ₃	0.54
K ₂ O	0.09
LOI	1.24

Supplier:

Womersley's Limited
Walkley Lane
Heckmondwike
West Yorkshire
WF16 0PG
Tel 01924 400651
Fax 01924 403489
www.womersleys.co.uk