

NOSTERFIELD WASHED RIVER SAND

GRADATION ANALYSIS TEST REPORT

Source:NOSTERFIELD

Material Type: Drystone Aggregate

Test Method: Wash grading to BS 812 : Section 103.1: 1985

SAMPLE ANALYSIS

Sieve Size	Percent Passing
8mm	100
6.3mm	100
4mm	97
1mm	80
500 µm	59
250 µm	21
63 µm	1

Moisture content = 9.2%

Supplier:

Womersley's Limited
Walkley Lane
Heckmondwike
West Yorkshire
WF16 0PG
Tel 01924 400651
Fax 01924 403489
www.womersleys.co.uk